

Document Summary

Detail Type	Detail
Event	000009839
Commodity	Gloss Text Sheets
Attachment	2
Group-Class	75-47
Bid Specification	9310-3812
Revision Level	6
Revision Date	June 14, 2018
Agency Name	Statewide

Revision History

Bid Spec	Rev Level	Revision Date	Author	Summary of Changes
9310-3812	6	June 14, 2018	Maduell, R.	Bid development



Table of Contents

Document Summary	1
Document SummaryRevision History	1
Table of Contents	2
1.0 SCOPE	
2.0 APPLICABLE LAWS and INDUSTRY STANDARDS	
2.1 LAWS and REGULATIONS	
2.2 INDUSTRY STANDARDS	3
3.0 TECHNICAL REQUIREMENTS	
3.1 CONFIGURATION	3
TABLE 1: PAPER WEIGHT AND SIZES	3
3.2 MATERIAL	3
3.3 TABLE 2: CHARACTERISTICS	
3.4 PERFORMANCE	
3.5 WORKMANSHIP	
4.0 ENVIRONMENTALLY PREFERABLE PURCHASING (EPP)	
4.0 ENVIRONMENTALLTTREFERABLET OROHASING (LTT)	



1.0 SCOPE

This specification describes archival quality acid free, plain coated, gloss text paper suitable for use in offset and digital presses.

2.0 APPLICABLE LAWS and INDUSTRY STANDARDS

Specifications and standards referenced in this document in effect on the opening of the Invitation for Bid form a part of this specification where referenced.

- 2.1 LAWS and REGULATIONS
 None listed
- 2.2 INDUSTRY STANDARDS
 None listed

3.0 TECHNICAL REQUIREMENTS

3.1 CONFIGURATION

The gloss sheets shall be available in the following weights and sizes:

TABLE 1: PAPER WEIGHT AND SIZES

WEIGHT, grade	SIZE, inches	COLOR	
60 pound	8.5 to 40	White	
70 pound	8.5 to 40	White	
80 pound	8.5 to 40	White	
100 pound	8.5 to 40	White	

Dimensional tolerance shall be ± 0.063 inches (± 1.6 mm) either direction. Adjacent sheets in carton shall not vary more than 0.015 inches (0.4 mm) from each other. Mill converted and packaged inventory only.

3.2 MATERIAL

The gloss paper shall be a commercial or industrial grade paper which, after being taken or rolled off paper making machine, undergoes no further process or treatment other than calendaring cutting and packaging. Sheet sizes less than 19 by 25 inches shall be digitally guaranteed paper.



3.3 TABLE 2: CHARACTERISTICS

The paper shall demonstrate the following characteristics:

	TAPPI	Requirements	Requirements	Requirements	Requirements
CHARACTERISTIC	METHOD	for 60 pound	for 70 pound	for 80 pound	for 100 pound
Basis Weight in pounds	T410	60	70	80	100
Minimum Caliper in mils	T411	2.8	3.2	3.7	4.7
Minimum Brightness %	T452	91	91	91	91
Minimum Whiteness	CIE	92	92	92	92
Minimum Opacity %	T425	90	91	93	94
Minimum Paper Gloss	T480	67	67	67	67
Minimum Postconsumer					
Recycled Content	N/A	10	10	10	10

3.4 PERFORMANCE

- 3.4.1 The paper shall perform satisfactorily in the various printing operations it is subjected to (i.e., printing, folding, slitting, collating, perforating, etc.).
- 3.4.2 The paper shall be suitable for use on high speed offset presses.
- 3.4.3 The paper shall lie flat on machine feed and collator surfaces before and after application of single side and back-to-back reproductions.
- 3.4.4 The paper shall demonstrate either a workable curl that can be overcome under reasonable working conditions or no tendency to curl.
- 3.4.5 The paper shall provide essentially trouble free performance.

3.5 WORKMANSHIP

- 3.5.1 The paper stock shall be free from defects which degrade appearance, performance and serviceability.
- 3.5.2 The paper surfaces shall be free from lint, fuzz, wrinkles, waviness, folds, holes, tears, and other detrimental defects.
- 3.5.3 The paper shall be furnished in the sizes ordered.
- 3.5.4 Grain of paper shall be long unless otherwise specified in the Invitation for Bid (IFB).
- 3.5.5 Natural curl of paper shall be minimal and away from wire side. Curl shall not hinder papers intended use.

4.0 ENVIRONMENTALLY PREFERABLE PURCHASING (EPP)

4.1 SUSTAINABILITY CERTIFICATION

The product shall comply at a minimum with one of the following:

- Forest Stewardship Council (FSC) Chain of Custody certification
- Sustainable Forest Initiative (SFI) Chain of Custody certification
- Programme for the Endorsement of Forest Certification (PEFC) Chain of Custody certification